

Super Duplex 2507 stainless steel alloy provides improvements in strength and corrosion resistance over Duplex 2205. Known for their high yield strength, Super Duplex bolts offers twice that of annealed austenitic stainless steels, like 304 and 316. Super Duplex provides excellent resistance to localized attack from chloride environments. Grade 2507 fasteners also provide corrosion protection from organic acids such as formic and acetic acid. They are used for mechanical assemblies and infrastructure for strength and seawater resistance, as well as water systems and desalinization plants that require protection from saltwater.

Properties

Ultimate Tensile Strength	125 ksi
Yield Strength at 0.2%	82 ksi
Elongation %	40
Usable Temperature Limit	570°F / 300°C

Key Benefits

- Excellent localized resistance to pitting, erosion and crevice corrosion, as well as corrosion fatigue
- Excellent localized resistance to chloride
- Very high mechanical strength
- High thermal conductivity
- Low coefficient of thermal expansion

Chemistry & Specifications

Super Duplex 2507	Fe	Cr	Ni	Мо	Mn	Si	Р	С	S
Typical	-	25.0	7	4	≤1.2	≤0.8	≤0.015	≤0.030	≤0.015

SPECIFICATIONS: EN 10216-5, ASTM A789; A790, ASTM A182 ASTM A182, ASTM A815, ASTM A240, EN 10088-2, ASTM A479, EN 10088-3 EN 10088, ISO 15156-3, NACE MR0175, Werkstoff 1.4410 S.Duplex

Material Data

SUPER DUPLEX 2507 - Tensile Data							
Temperature (°F)	Ultimate Tensile (ksi)	Yield Strength at 0.2% Offset	Elongation %				
Room Temp.	116	80	15				
212	101	65	12				
302	98	61	2.5				
392	95	58	12				
482	94	55	1-				

Our Engineers Are Here to Help